DRAFT FOR DEVELOPMENT

DD ENV ISO 8502-1:2001

Incorporating Amendment No.1 to DD 207:1992 (renumbers the DD as DD ENV ISO 8502-1:2001)

Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness —

Part 1: Field test for soluble iron corrosion products

ICS 87.020

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

Committees responsible for this Draft for Developement

The preparation of this Draft for Development was entrusted by the Pigments, Paints and Varnishes Standards Policy Committee (PVC/-) to Technical Committee PVC/21, upon which the following bodies were represented:

Association of Consulting Engineers
British Chemical Engineering Contractors Association
British Constructional Steelwork Association Ltd.
British Gas plc
British Grit Association
British Maritime Technology
British Railways Board
British Steel Industry
Corrosion Control Engineering Joint Venture
Department of Transport
Electricity Industry in United Kingdom
Institute of Corrosion
National Federation of Painting and Decorating Contractors
Oil and Colour Chemists Association
Paint Research Association
Paintmakers' Association of Great Britain Ltd.
RAFRA Technology Ltd.
Royal Society of Chemistry

This Draft for Development, having been prepared under the direction of the Pigments, Paints and Varnishes Standards Policy Committee, was published under the authority of the Standards Board and comes into effect on
31 January 1992

© BSI 03-2001

The following BSI reference relates to the work on this Draft for Development:
Committee reference STI/21

ISBN 0 580 20492 8

Amendments issued since publication

Amd. No.	Date	Comments
10892	March 2001	Implementation of the European Standard

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

Contents

		Page
Committees responsible		Inside front cover
National foreword		ii
Introduction		1
1	Scope	2
2	Normative references	2
3	Principle	2
4	Reagents, apparatus and materials	2
5	Procedure	3
6	Expression of results	3
7	Test report	3
Annex A (informative) Other methods of determining soluble iron corrosion products		4
Annex ZA (normative) Normative references to international publications with their relevant European publications		5

© BSI 03-2001

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

National foreword

This publication is not to be regarded as a British Standard.

It is being issued in the Draft for Development series of publications and is of a provisional nature because it is considered that further experience is required in its application before it is converted into a British Standard. It should be applied on this provisional basis, so that information and experience of its practical application may be obtained.

Comments arising from the use of this Draft for Development are requested so that UK experience can be reported to the European organization responsible for its conversion into a European Standard. A review of this publication will be

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

STD.BSI DD ENV ISO 8502-1-ENGL 2001 ■ 1624669 0896116 119 ■

EUROPEAN PRESTANDARD
PRÉNORME EUROPÉENNE
EUROPÄISCHE VORNORM

ENV ISO 8502-1

July 1999

ICS 87.020

English version

Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 1: Field test for soluble iron corrosion products

(ISO/TR 8502-1:1991)

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés — Essais pour apprécier la propreté d'une surface —
Partie 1: Essai in situ pour déterminer les produits de corrosion du fer
(ISO/TR 8502-1:1991)

Vorbereitung von Stahloberflächen vor dem Auftragen von Beschichtungsstoffen — Prüfungen der Oberflächenreinheit —
Teil 1: Feldprüfung auf lösliche Korrosionsprodukte des Eisens
(ISO/TR 8502-1:1991)

This European Prestandard (ENV) was approved by CEN on 7 June 1999 as a prospective standard for provisional application.

The period of validity of this ENV is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particulary on the question whether the ENV can be converted into a European Standard.

CEN members are required to announce the existence of this ENV in the same way as for an EN and to make the ENV available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the ENV) until the final decision about the possible conversion of the ENV into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

© 1999 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. ENV ISO 8502-1:1999 E

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

Foreword

The text of the International Technical Report from Technical Committee ISO/TC 35, Paints and varnishes, of the International Organization for Standardization (ISO) has been taken over as a European Prestandard by Technical Committee CEN/TC 139, Paints and varnishes, the Secretariat of which is held by DIN.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Prestandard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom

NOTE Normative references to International Standards are listed in Annex ZA (normative).

© BSI 03-2001

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

Introduction

The performance of protective coatings of paint and related products applied to steel is significantly affected by the state of the steel surface immediately prior to painting. The principal factors that are known to influence this performance are:

a) the presence of rust and mill scale;
b) the presence of surface contaminants, including salts, dust, oils and greases;
c) the surface profile.

International Standards ISO 8501, ISO 8502 and ISO 8503 have been prepared to provide methods of assessing these factors, while ISO 8504 provides guidance on the preparation methods that are available for cleaning steel substrates, indicating the capabilities of each in attaining specified levels of cleanliness.

These International Standards do not contain recommendations for the protective coating systems to be applied to the steel surface. Neither do they contain recommendations for the surface quality requirements for specific situations even though surface quality can have a direct influence on the choice of protective coating to be applied and on its performance. Such recommendations are found in other documents such as national standards and codes of practice. It will be necessary for the users of these International Standards to ensure that the qualities specified are:

— compatible and appropriate both for the environmental conditions to which the steel will be exposed and for the protective coating system to be used;

— within the capability of the cleaning procedure specified.

The four International Standards referred to above deal with the following aspects of preparation of steel substrates:

ISO 8501 — *Visual assessment of surface cleanliness;*

ISO 8502 — *Tests for the assessment of surface cleanliness;*

ISO 8503 — *Surface roughness characteristics of blast-cleaned steel substrates;*

ISO 8504 — *Surface preparation methods.*

Each of these International Standards is in turn divided into separate parts.

Rusted steel substrates, particularly of rust grades C or D (see ISO 8501-1), even when blast-cleaned to preparation grade Sa 3 (see ISO 8501-1 and ISO 8501-2), may still be contaminated by soluble iron corrosion products. These compounds are almost colourless and are localized at the lowest point of the rust pits. If they are not removed prior to painting, chemical reactions can result in large accumulations of rust which destroy the adhesion between the substrate and the applied protective coating.

In surfaces cleaned to preparation grades lower than Sa 2½, it is likely that soluble iron corrosion products will be concealed under layers of iron oxide and will not be detectable until further cleaning is carried out.

In the field, it is difficult to determine accurately the concentration of soluble salts on the substrate present after blast-cleaning. Nevertheless, because a procedure is required for detecting and estimating soluble iron salts, one is described in this type 2 Technical Report. It is given as an aid and is not, at this stage, to be considered as an International Standard, as further experience needs to be gained with the method.

In addition to the procedure described in this Technical Report, other methods of detecting soluble salts are in use, and some of these are described briefly in Annex A with a commentary on their advantages and limitations.

Using the swabbing procedures described in clause **5**, it has been estimated that the surface concentration detectable is of the order of 10 mg/m2 of iron(II) ions. In practical use, there are indications that results obtained in the field of less than 15 mg/m2 are probably insignificant for most coating purposes, but that results of the order of 250 mg/m^2 indicate that it would be undesirable to paint the surface, except if the coated structure is to be maintained in the very driest exposure conditions. Surfaces indicating this latter level of contamination will also generally rapidly re-rust after blast-cleaning in relative humidities above 50 %.

NOTE 1 After carrying out the test, it is advisable to further clean the test area to remove flash rusting before application of a paint system.

It is important, when specifying the maximum permissible amount of surface contamination by soluble iron corrosion products, to avoid imposing unnecessarily strict limits. Lower limits are appropriate only to marine or similar aggressive environments. A requirement for excessively low contamination levels can be very costly and, in many rural and non-industrial inland areas, would be disproportionate to the benefits to be obtained.

© BSI 03-2001

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

1 Scope

This Technical Report describes a field test for the assessment of soluble iron corrosion products on surfaces abrasively blast-cleaned to Sa 2½ or better (see ISO 8501-1 or ISO 8501-2). The test uses indicator test strips that are sensitive to ferrous ions.

This field test is not applicable to manually cleaned steel surfaces.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Technical Report. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this Technical Report are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 3696:1987, Water for analytical laboratory use — Specification and test methods

ISO 8501-1:1988, Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings

ISO 8501-2 Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 2: Preparation grades of previously coated steel substrates after localized removal of previous coatings[1)].

3 Principle

A proportion of the soluble salts on the test substrate is removed by controlled washing of the surface with

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

5 Procedure

5.1 Preparation of reference indicator test strips

Calibrate indicator test strips (**4.1**) for reference use immediately before each series of tests, using the following procedure.

Prepare fresh solutions of soluble iron(II) salt (**4.2**) with iron(II) concentrations of 5 mg/l, 10 mg/l, 100 mg/l and 250 mg/l and stabilize with dilute sulfuric acid (**4.3**). If the stability of the soluble iron(II) salt is questionable, determine its iron(II) content by any standard redox method prior to making up the solutions. Into each solution, dip an indicator test strip (**4.1**), and withdraw and retain for comparison with strips obtained during the test.

5.2 Preparation of the test solution

Carry out the washing procedure described below and the subsequent assessment of the resulting test solution (see **5.3**) in duplicate. Minimize contamination with iron salts by wearing clean plastic gloves or by using plastic tweezers, as appropriate.

Following blast-cleaning, mark out a test area measuring approximately 25 000 mm^2 (e.g. 250 mm × 100 mm) using a suitable means (**4.7**). Soak an absorbent cotton pad (**4.4**) with the water in the first container (**4.5**a) and then thoroughly swab the test area with the soaked pad. Take care to avoid water running freely from the pad, especially if the test area is not horizontal. Place the absorbent cotton swab into the second container (**4.5**b) and repeat the swabbing procedure with a fresh cotton pad. Add any remaining water in the first container to the second container.

Complete the whole swabbing operation in approximately 4 min.

Dry the surface with a dry absorbent cotton pad and place the pad in the second container. Thoroughly mix the three absorbent cotton pads and water, using the glass rod (**4.6**), to prepare the test solution.

5.3 Assessment of the test solution

Dip an indicator test strip (**4.1**) into the test solution prepared in **5.2** in the second container (**4.5**b) and assess the colour against the reference indicator strips (see **5.1**).

6 Expression of results

Using 50 ml of water and a test area of 25 000 mm^2 as described in **5.2**, twice the iron(II) concentration, in milligrams per litre, indicated by the indicator strip is equal to the concentration of dissolved iron(II) corrosion products in milligrams per square metre.

7 Test report

The test report shall contain at least the following information:

a) a reference to this Technical Report (ISO/TR 8502-1);

b) identification and attitude (e.g. horizontal, vertical, angled) of the area tested;

c) the rust grade and preparation grade of the surface under test;

d) any deviation from the test method specified;

e) the result of the test as indicated in clause **6**;

f) the date(s) of the test.

© BSI 03-2001

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

Annex A (informative)
Other methods of determining soluble iron corrosion products

A.1 General

Recent work in the UK has indicated that the semi-quantitative method of test for ferrous ions, using a swab test for sampling and using test strips that are specific to iron(II) ions (as given in this Technical Report), remains the most suitable for a field test. In addition, soluble-salt contamination on a steel surface is unlikely to be uniformly distributed but largely concentrated in individual pits. The analytical technique requires sampling of a substantial surface area, about 25 000 mm^2, which could give an assessment of the average contamination of the surface but fail to reveal the presence of pits containing a high concentration of aggressive material.

A number of other field tests for the detection of these salts have been investigated over the past years. These are described in **A.2**, **A.3**, **A.4** and **A.5**.

A.2 Conductivity measurement

This method measures the conductivity of water washings from the blast-cleaned surface. An increase in conductivity could be correlated with the soluble-salt content. This method has the advantage of measuring all soluble salts, e.g. ammonium as well as ferrous. It has the disadvantage of requiring special apparatus for field use.

A.3 Potassium hexacyanoferrate(III) test papers

This method uses test papers impregnated with potassium hexacyanoferrate(III) to indicate the presence of soluble iron salts. The test, described in Appendix G of BS 5493:1977, *Code of Practice for protective coating of iron and steel structures against corrosion,* is as follows.

a) Spray a fine mist of water droplets on to a small area of blast-cleaned surface using a hand spray (a scent-spray type of bottle is satisfactory).

b) Allow the water droplets to evaporate and at the moment when they have disappeared but the surface is just perceptibly wet apply a small piece of the test paper and press with the thumb for 2 s to 5 s.

If soluble salts remain, these will be drawn by capillary action into the test paper and will react with the potassium hexacyanoferrate(III) to give "a characteristic prussian blue complex as blue dots on the paper, corresponding to the contaminated pits on the blast-cleaned steel".

The method is simple to use and has the advantage of indicating the exact location of pits containing soluble iron corrosion products. It has the disadvantage that it relies on wetting the surface to the right degree in order to dissolve the salts. Too little water and this will not be achieved, too much water and there is an overall blue coloration over the test paper. Also, the intensity of the blue spots varies according to the sampling procedure and the intensity may remain consistently high even when the actual soluble salt contamination has dropped to a low level. In addition, the test papers deteriorate rapidly during storage and have to be freshly made for each test.

A.4 Corrosion-product indicators in emulsion-type formulations

This method incorporates soluble iron corrosion product indicators, such as potassium hexacyanoferrate(III) or 2,2′-bipyridyl, in a white emulsion-type formulation. This has the possible advantage over the potassium hexacyanoferrate(III) test papers in that the sampling technique may be more efficient. However, the method has the other disadvantages of the potassium hexacyanoferrate(III) method. It can give an overall blue coloration unrelated to the degree of contamination, and it has been found that the indicator deteriorates in storage.

Similarly, if a thick film of a specially formulated white emulsion paint is applied over a contaminated surface, the presence of soluble iron salts is demonstrated by a pattern of flash-rusting developing in the film. As far as is known, no repeatability or reproducibility tests have been carried out on this method but it is understood that it is used by some coating applicators as a "pass/fail" test for critical applications.

A.5 Visual inspection using an illuminated magnifier

This method uses an illuminated magnifier with × 20 magnification. Whitish crystals of corrosion products can often be seen in the pits of the blast-cleaned surface. The disadvantage of the method is that it is very subjective and gives no indication of the nature and composition of the contamination. In addition, the crystals may dissolve at high humidities and therefore not be visible.

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

Annex ZA (normative)
Normative references to international publications with their relevant European publications

This European Prestandard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

Publication	Year	Title	EN	Year
ISO 3696	1987	*Water for analytical laboratory use — Specification and test methods*	EN ISO 3696	1995

© BSI 03-2001

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services

DD ENV ISO 8502-1:2001

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001. Standards are also available from the BSI website at http://www.bsi-global.com.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001. Further information about BSI is available on the BSI website at http://www.bsi-global.com.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.

BSI
389 Chiswick High Road
London
W4 4AL

COPYRIGHT British Standards Institute on ERC Specs and Standards
Licensed by Information Handling Services