BRITISH STANDARD

BS EN ISO 8502-2:2000

BS 7079-B2: 1992

Incorporating Amendment No. 1 to BS 7079-B2:1992 (renumbers the BS as BS EN ISO 8502-2:2000)

Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness —

Part 2: Laboratory determination of chloride on cleaned surfaces

The European Standard EN ISO 8502-2:2000 has the status of a British Standard.

ICS 17.040.20; 25.220.10

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

Committees responsible for this British Standard

The preparation of this British Standard was entrusted by the Pigments, Paints and Varnishes Standards Policy Committee (PVC/-) to Technical Committee PVC/21, upon which the following bodies were represented:

Association of Consulting Engineers
British Chemical Engineering Contractors' Association
British Constructional Steelwork Association Ltd.
British Gas plc
British Grit Association
British Railways Board
British Steel Industry
Department of Transport
Electricity Association
Institute of Corrosion
National Federation of Painting and Decorating Contractors
Oil and Colour Chemists' Association
Paint Research Association
Paintmakers Association of Great Britain Ltd.
Royal Society of Chemistry

This British Standard, having been prepared under the direction of the Pigments, Paints and Varnishes Standards Policy Committee, was published under the authority of the Standards Board and comes into effect on 15 November 1992

© BSI 06-2000

The following BSI references relate to the work on this standard:
Committee reference PVC/21
Draft for comment 87/55818 DC

ISBN 0 580 21196 7

Amendments issued since publication

Amd. No.	Date	Comments
10591	June 2000	Renumbers BS 7079-B2:1992 as BS EN ISO 8502-2:2000

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

Contents

		Page
Committees responsible		Inside front cover
National foreword		ii
Introduction		1
1	Scope	1
2	Normative references	2
3	Principle	2
4	Reagents	2
5	Apparatus and materials	3
6	Procedure	3
7	Expression of results	3
8	Test report	4
Annex ZA		5

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS
Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

National foreword

This British Standard is the English language version of EN ISO 8502-2:2000. It is dual-numbered as BS 7079-B2:1992. It is identical with ISO 8502-2:1992.

Cross references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled "International Standards Correspondence Index", or by using the "Find" facility of the BSI Standards Electronic Catalogue.

This standard makes an informative reference to ISO 8501-2, which is in preparation. It is envisaged that when ISO 8501-2 is published it will be implemented, dual-numbered, as BS 7079-A2.

Further information on the ISO 8501, ISO 8502, ISO 8503 and ISO 8504 series of standards is given in BS 7079 *Preparation of steel substrates before application of paints and related products. Part 0. Introduction*.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, the EN foreword page, the EN title page, pages 1 to 5 and a back cover.

The BSI copyright notice displayed in this document indicates when the document was last issued.

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN ISO 8502-2

April 1999

ICS 87.020

English version

Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 2: Laboratory determination of chloride on cleaned surfaces

(ISO 8502-2:1992)

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés — Essais pour apprécier la propreté d'une surface —
Partie 2: Recherche des chlorures sur les surfaces nettoyées
(ISO 8502-2:1992)

Vorbereitung von Stahloberflächen vor dem Auftragen von Beschichtungsstoffen — Prüfungen der Oberflächenreinheit —
Teil 2: Laborbestimmung von Chlorid auf gereinigten Oberflächen
(ISO 8502-2:1992)

This European Standard was approved by CEN on 1 April 1999.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

© 1999 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.
Ref. No. EN ISO 8502-2:1999 E

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

Foreword

The text of the International Standard from Technical Committee ISO/TC 35, Paints and varnishes, of the International Organization for Standardization (ISO) has been taken over as a European Standard by Technical Committee CEN/TC 139, Paints and varnishes, the Secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 1999, and conflicting national standards shall be withdrawn at the latest by October 1999.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

--`,,```,,,,````-`-`,,`,,`,`,,`---
Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

Introduction

The performance of protective coatings of paint and related products applied to steel is significantly affected by the state of the steel surface immediately prior to painting. The principal factors that are known to influence this performance are:

a) the presence of rust and mill scale;

b) the presence of surface contaminants, including salts, dust, oils and greases;

c) the surface profile.

International Standards ISO 8501, ISO 8502 and ISO 8503 have been prepared to provide methods of assessing these factors, while ISO 8504 provides guidance on the preparation methods that are available for cleaning steel substrates, indicating the capabilities of each in attaining specified levels of cleanliness.

These International Standards do not contain recommendations for the protective coating systems to be applied to the steel surface. Neither do they contain recommendations for the surface quality requirements for specific situations even though surface quality can have a direct influence on the choice of protective coating to be applied and on its performance. Such recommendations are found in other documents such as national standards and codes of practice. It will be necessary for the users of these International Standards to ensure that the qualities specified are:

— compatible and appropriate both for the environmental conditions to which the steel will be exposed and for the protective coating system to be used;

— within the capability of the cleaning procedure specified.

The four International Standards referred to above deal with the following aspects of preparation of steel substrates:

ISO 8501 — *Visual assessment of surface cleanliness;*

ISO 8502 — *Tests for the assessment of surface cleanliness;*

ISO 8503 — *Surface roughness characteristics of blast-cleaned steel substrates;*

ISO 8504 — *Surface preparation methods.*

Each of these International Standards is in turn divided into separate parts.

This part of ISO 8502 describes a method for the assessment of chloride-containing salts that are readily soluble in water and are present on a steel surface.

Rusted steel substrates, particularly of rust grades C or D (see ISO 8501-1), even when blast-cleaned to preparation grade Sa 3 (see ISO 8501-1 and ISO 8501-2), may still be contaminated by soluble salts and corrosion products. These compounds are almost colourless and are localized at the lowest point of the rust pits. If they are not removed prior to painting, chemical reactions can result in large accumulations of rust that destroy the adhesion between the substrate and the applied protective coating.

Even if the salt is readily soluble in water, it is often impossible to remove it completely from the surface by a simple washing such as that described in this procedure. The method does not therefore determine the total amount of chloride on the surface but gives an indication of the cleanliness level of the surface. Careful scraping of the surface with a metal spatula or knife during the washing, and prolonging the washing time, should remove a larger proportion of the salt.

WARNING — The procedure described in this part of ISO 8502 is intended to be carried out by qualified chemists or by other suitably trained and/or supervised personnel. The substances and procedures used in this method may be injurious to health if adequate precautions are not taken. Attention is drawn in the text (see 4.4) to certain specific hazards. This part of ISO 8502 refers only to its technical suitability and does not absolve the user from statutory obligations relating to health and safety.

1 Scope

This part of ISO 8502 describes a method for assessment of chloride-containing salts that are readily soluble in water and are present on a steel surface. The method is also applicable to previously coated surfaces. It is normally to be used in a laboratory using washings sampled from surfaces on site.

The method is applicable to the assessment of salts that have been introduced by the cleaning procedure, or that have deposited on the surface before or after the cleaning.

NOTE 1 Although the procedure for chloride determination is generally accurate, the overall precision of the method is limited by uncertainties in the sampling procedure. In addition, traces of iron chloride at the bottom of pits are difficult to extract into the sample.

--`,,``,`````,,`,,,,,,,,`````-`-`,,`,,`,`,,`---

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS
Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

The test method cannot be used on surfaces treated with chromate or nitrite, which are commonly used as inhibitors in the water when wet blast-cleaning. This is because a chromate concentration of 10 mg/l or greater or a nitrite concentration of 20 mg/l or greater in the wash water interferes with the determination of the chloride.

An iron(III) ion concentration of 10 mg/l also interferes with the determination, but the iron(III) ions are concentrated in the rust deposits, which are removed from the test solution by filtration.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 8502. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 8502 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods.*

ISO 8501-1:1988, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings.*

ISO 8501-2[1)], *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 2: Preparation grades of previously coated steel substrates after localized removal of previous coatings.*

3 Principle

A defined area of the steel surface is washed with a known volume of water and the chloride in the wash water is titrated with mercury(II) nitrate using a diphenylcarbazone/bromophenol blue mixed-indicator titration method developed by Clarke[2)]. In the titration, mercury ions react with free chloride ions to form $HgCl_2$ which dissociates only slightly. When the chloride ions are consumed, the excess mercury ions give an intense violet colour with diphenylcarbazone, thus indicating the end-point of the titration.

4 Reagents

During the analysis, use only reagents of recognized analytical grade and water of at least grade 3 purity in accordance with ISO 3696.

4.1 *Nitric acid, c*(HNO_3) about 0,05 mol/l.

Add 3,5 ml of concentrated nitric acid (ρ = 1,40 g/ml) to some water, and make up to 1 000 ml with water.

4.2 *Sodium hydroxide solution, c*(NaOH) about 0,025 mol/l.

Dissolve 1,0 g of sodium hydroxide in water, transfer to a 1 000 ml volumetric flask and make up to the mark with water.

4.3 *Potassium chloride,* standard solution, ρ(Cl) = 100 mg/l.

Dissolve 0,210 3 g of potassium chloride in water, transfer to a 1 000 ml volumetric flask and make up to the mark with water.

1 ml of this solution contains 0,1 mg of Cl.

4.4 *Mercury(II) nitrate,* standard volumetric solution, *c*[$Hg(NO_3)_2$] = 0,012 5 mol/l.

WARNING — Mercury(II) nitrate is toxic. Avoid contact with eyes and skin.

4.4.1 *Preparation*

Dissolve 4,171 g of mercury(II) nitrate hemihydrate, [$Hg(NO_3)_2.0{,}5H_2O$] in water, transfer to a 1 000 ml volumetric flask and make up to the mark with water.

4.4.2 *Standardization*

Introduce by means of a pipette (**5.11**) into a beaker (**5.5**) a 20 ml aliquot of the potassium chloride standard solution (**4.3**). Add 5 drops of the diphenylcarbazone/bromophenol blue mixed-indicator solution (**4.5**) and stir. If a blue-violet or red colour develops, add nitric acid (**4.1**) dropwise until the colour changes to yellow and then add 1 ml excess of nitric acid. If a yellow or orange colour forms immediately on the addition of the indicator, obtain the blue-violet colour by adding sodium hydroxide solution (**4.2**) dropwise. Then proceed with the acidification. Titrate the yellow acidified solution with the mercury(II) nitrate solution (**4.4**) until a blue-violet colour persists throughout the solution. Retain the titrated solution for comparison with the blank titrated solution obtained in **6.1**. Calculate the concentration of the mercury(II) nitrate solution. Note that 1 mol of mercury(II) ions is equivalent to 2 mol of chloride ions.

[1)] To be published.

[2)] CLARKE, F.E.: Determination of chloride in water, *Analytical Chemistry*, 22 (1950), 4, pp. 553-555.

© BSI 06-2000

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

4.5 *Diphenylcarbazone/bromophenol blue,* mixed-indicator solution.

Dissolve 0,5 g of crystalline diphenylcarbazone and 0,05 g of crystalline bromophenol blue in 75 ml of ethanol, 95 % (*V*/*V*), and make up to 100 ml with ethanol.

Store in a brown bottle.

5 Apparatus and materials

5.1 *Ruler* and *essentially chloride-free chalk,* other suitable means for marking the test area.

5.2 *Absorbent cotton pads (cotton wool),* of mass 1 g to 1,5 g.

5.3 *Metal spatula* or *knife.*

5.4 *Gloves,* of plastics material.

5.5 *Beakers,* of capacity 250 ml.

5.6 *Small glass rod.*

5.7 *Funnel.*

5.8 *Filter paper,* approximately 120 mm diameter.

5.9 *Measuring cylinder,* of capacity 50 ml.

5.10 *Volumetric flasks,* of capacity 50 ml, 100 ml and 1 000 ml.

5.11 *Volumetric pipettes,* of capacity 1 ml and 20 ml.

5.12 *Device for titration,* preferably a digital titrator.

6 Procedure

6.1 Blank titration

Carry out a blank titration each time on water, retaining the titrated solution for comparison of end-points. Follow the procedure described in **4.4.2** but using 20 ml of water instead of the potassium chloride solution.

6.2 Washing of the surface

Carry out the test at least in duplicate. During the swabbing procedure, ensure absence of accidental contamination of the wash water by using, for example, clean plastic gloves (**5.4**).

Mark out a test area measuring approximately 25 000 mm^2 (for example 250 mm × 100 mm) using the ruler and chalk or other suitable means (**5.1**).

Mark two beakers (**5.5**) A and B. Pour 45 ml of water into beaker A, using the measuring cylinder (**5.9**). Soak an absorbent cotton pad (**5.2**) in the water and thoroughly swab the test area with the pad. Do not allow water to drip from the pad or run off the test area. Remove the water from the surface with the absorbent cotton pad and squeeze the washings into beaker B.

In the case of bare steel, scrape the surface with the metal spatula or knife (**5.3**) until bright metal is exposed over at least 50 % of the test area.

Repeat the swabbing procedure with several portions of water and, if the pad is worn out, use a fresh one, continuing in this way until all the water has been used up. Keep the used absorbent cotton pads. The swabbing procedure should take at least 5 min.

Filter the washings, using the filter paper (**5.8**) and the funnel (**5.7**), and collect the filtrate in the volumetric flask of capacity 50 ml (**5.10**). Wash the used absorbent cotton pads and the filter papers with small portions of water (total 5 ml), using beaker B and the small glass rod (**5.6**). Squeeze the pads and collect the washings in the flask. Make up to the mark with water.

6.3 Wash-water titration

Carefully shake the 50 ml volumetric flask. Using a pipette (**5.11**), transfer 20 ml of the wash water into a clean beaker (**5.5**). Determine the chloride content by following the procedure given in **4.4.2** but using the wash water.

7 Expression of results

Calculate the assessed amount of chloride per unit surface area, $\rho_A(\mathrm{Cl})$, expressed in milligrams per square metre, using the equation:

$$\rho_A(\mathrm{Cl}) = \frac{(V_1 - V_0)c \times 1{,}773 \times 10^8}{A}$$

where

V_1 is the volume, expressed in millilitres, of the mercury(II) nitrate solution used for the titration of the wash water (see **6.3**);

V_0 is the volume, expressed in millilitres, of the mercury(II) nitrate solution used for the blank titration (see **6.1**);

c is the actual concentration, expressed in moles of $Hg(NO_3)_2$ per litre, of the mercury(II) nitrate solution, as determined in **4.4.2**;

A is the surface area washed, expressed in square millimetres.

Report each result to the nearest 10 mg/m^2.

NOTE 2 The performance of a paint system is affected by the amount of soluble chloride remaining on the surface. The acceptable level of this contamination is related to the service conditions. Experience in the use of this method is limited and more will be needed before limits can be specified in connection with its use.

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS
Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

8 Test report

The test report shall contain at least the following information:

a) all details necessary to identify the surface tested, including details of shape and attitude (e.g. horizontal, vertical, at an angle);

b) a reference to this part of ISO 8502 (ISO 8502-2);

c) the results of the test, as indicated in clause **7**;

d) any deviation from the test method specified;

e) the date(s) of the test.

© BSI 06-2000

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

Annex ZA (normative)
Normative references to international publications with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publicatgion referred to applies.

Publication	Year	Title	EN	Year
ISO 3696	1987	*Water for analytical laboratory use — Specification and test methods*	EN ISO 3696	1995

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS
Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 020 8996 9000. Fax: 020 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 020 8996 9001. Fax: 020 8996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 020 8996 7111. Fax: 020 8996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 020 8996 7002. Fax: 020 8996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 020 8996 7070.

BSI
389 Chiswick High Road
London
W4 4AL

Copyright British Standards Institution
Reproduced by IHS under license with BSI - Uncontrolled Copy
No reproduction or networking permitted without license from IHS

Licensee=LOC 1-Houston TX/5919206101, User=wang, jingang
Not for Resale, 11/10/2005 22:22:54 MST